

Neopor® Packaging Technical Bulletin

Recommendations for packaging, transporting, storing and installing building insulation products

Notice:

External factors, such as solar energy conveyed via reflective surfaces, can create excessive heat build-up within insulation products made of Neopor® GPS foam. Excessive heat-build-up can damage insulation products made of Neopor® GPS foam. Precautionary measures taken in the packaging, storage, transportation and installation of insulation products made of Neopor® GPS foam can help minimize the potential for damage.

Packaging and Transportation

- Insulation products and foam surfaces should be protected at all times from reflected sunlight and prolonged solar exposure.
- It is strongly recommended that insulation products be protected during storage and transportation with corrugated and/or white opaque film only.
- Transparent plastic wrapping film and clear adhesive tape or strap banding SHOULD NOT be used for packaging insulation products made of Neopor® GPS foam.

We Strongly Recommend:

- A white opaque 4 mil poly bag be used for EIFS packaging protection:
 - Reference: 4mil EIFS bags on rolls
Item number: 010.white.03 / 60 bags per roll
 - Typical dimensions of
25.5" x 20" x 78"
- If a white opaque film or shrink-wrap is being used, we recommend U-Line Type S-6019.

A supplier of Bags has been Identified:

Horizon Packaging
6224 Ringgold Rd,
Chattanooga, TN 37412
423-894-6050
Att. Wendy Bearden
wendyb@horizonpackaging.com

Please note: Bag dimension may vary by system supplier, please check system supplier board size requirements prior to ordering.

Job Site Storage:

Precautions taken when storing insulation products on the job site can help minimize the potential for damage. Care should be taken to keep exposed foam protected from reflected sunlight or prolonged solar exposure.

Installation:

During the construction process, avoid leaving insulation products and Neopor® foam surfaces uncovered in areas where 'reflected solar energy' is expected to be present, such as near metal or glass reflective surfaces.

THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH, AND ARE BASED ON BASF'S CURRENT KNOWLEDGE AND EXPERIENCE. THEY ARE PROVIDED FOR GUIDANCE ONLY, AND DO NOT CONSTITUTE THE AGREED CONTRACTUAL QUALITY OF THE PRODUCT OR A PART OF BASF'S TERMS AND CONDITIONS OF SALE. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE OF THE PRODUCT, BASF RECOMMENDS THAT THE READER CARRY OUT ITS OWN INVESTIGATIONS AND TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR ITS PARTICULAR PURPOSE PRIOR TO USE. IT IS THE RESPONSIBILITY OF THE RECIPIENT OF PRODUCT TO ENSURE THAT ANY PROPRIETARY RIGHTS AND EXISTING LAWS AND LEGISLATION ARE OBSERVED. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH HEREIN, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** ANY DESCRIPTIONS, DESIGNS, DATA AND INFORMATION GIVEN IN THIS PUBLICATION MAY CHANGE WITHOUT PRIOR INFORMATION. THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Neopor® is a trademark of BASF SE.
© 2017 BASF, Wyandotte, MI 48192. All rights reserved. BF-00000 11/17



BASF
We create chemistry